



PO Box 45746
 Atlanta, GA 30320
 P 877-697-5646
 www.rooflogos.com

LogoBondRM Repair Mastic is a tough, tenacious and durable white compound manufactured with high grade components. **LogoBondRM** was developed and is designed to be a superior material for new roofing, re-roofing and roof maintenance before installation of a roof logo. **LogoBondRM** is user friendly and can be applied using a brush, putty knife or trowel and has high pigment levels to provide superior hiding power.

BENEFITS: Reflective, easy to apply, product toughness and durability, elasticity, compatibility.

PRODUCT APPLICATION INCLUDES: Laps, cracks, seams, directional wall changes, screw heads, roof intrusions.

PRETREATMENT: Treat all surfaces with the appropriate LogoBond primer.

COVERAGE: 25-30 linear feet per gallon with 4" to 6" wide application.

CURE: Cures by ultra violet rays; allow for sufficient daylight. Cure time affected by environmental conditions.

STORAGE: In a clean, warm and well-ventilated area. Storage area temperature must be above 45°F.

CLEANUP: Clean tools with mineral spirits or paint thinner, if compound has dried. If compound is still wet, clean up with warm soapy water.

PRECAUTIONS: **DO NOT APPLY IF TEMPERATURE IS BELOW 55° F or above 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48-72 HOURS.** Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur. **DO NOT ALLOW PRODUCT TO FREEZE.** Do not heat container or store at temperatures greater than 120°F.

CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use.

DO NOT TAKE INTERNALLY!

If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

MAXIMUM V.O.C = 99 G/L

PHYSICAL PROPERTIES

Color.....	White
Elongation.....	560%
Percent Solids, Weight.....	67.8%
Application.....	Brush, Putty Knife, or Trowel
Recovery.....	94%
Weight per Gallon.....	11 lbs
Tensile Strength.....	213 psi
Viscosity.....	240 KU