



PO Box 45746
Atlanta, GA 30320
P 877-697-5646
www.rooflogos.com

LogoBondST Surface Treatment is a low viscosity, sprayable liquid used to pre-treat thermoplastic, EPDM rubber, and liquid applied roof membranes prior to power washing and application of LogoBondPRC or LogoBondCM. The unique chemistry of **LogoBondST** is designed for use with all LogoBond Coatings and significantly improves adhesion.

PREPARATION: Surface to be repaired or coated must be clean, dry and free of dust and dirt. The substrate must next be pressure washed with water at the rate of 2500 psi to remove remaining dust and dirt. **LogoBondST** is mandatory for maximum adhesion on newer thermoplastics and all EPDM substrates. Any residue of the **LogoBondST** left on the substrate will have negative adhesion results. Therefore a complete second rinse is essential.

APPLICATION: Apply with conventional compressive air sprayer.

COVERAGE: Approximately 1 gallon per 500 square feet.

PRECAUTIONS: Keep away from heat, sparks and open flame. In interior areas provide for proper ventilation or respiratory equipment. Use proper safety equipment.

WARNING: Avoid breathing fumes and prolonged contact with skin. Do not take internally.

DANGER! Harmful or fatal if swallowed. Do not induce vomiting. Call a physician immediately. Keep container covered when not in use. Do not thin. **DO NOT HEAT CONTAINER** or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use.

DO NOT TAKE INTERNALLY!

If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

MAXIMUM V.O.C = 0 G/L

PHYSICAL PROPERTIES

Appearance.....	Clear liquid
Color.....	Pink
Odor.....	Mild
PH.....	13-13.5
Density (WPG).....	8.46
Solubility in water.....	Completely soluble